

A large, golden pyramid stands in a vast desert landscape under a bright, hazy sky. The pyramid is constructed from many layers of stone blocks. In the foreground, there is a sandy dune. The entire scene is overlaid with a semi-transparent yellow triangle in the bottom right corner, which contains the product information text. The background is decorated with abstract, colorful geometric shapes and bokeh light effects in shades of yellow, orange, and red.

KC9820G

EGYPTIAN GOLD

Product Information

FROM ANCIENT HISTORY TO AVANT-GARDE

Green-gold reflection with a deep warm golden tone



The characteristics of KC9820G Egyptian Gold display an **exceptional strong covering green-gold tone**.



Egyptian Gold combines an intense and **vibrant green-gold reflection with a deep warm golden tone** when it is observed from a flat angle.



With powerful background coverage, KC9820G is a perfect option for **color intense, lively and high-value gold stylings**. It is based on synthetic mica (Fluorophlogopite), which exhibits and supports color purity, brightness and reflection power.

KC9820G EGYPTIAN GOLD

Optical Features	Special Product Features
Extended hiding power capabilities	Based on synthetic mica
Masstone in a warm gold tone	Suitable for all common applications for effect pigments
Reflection color with a green-gold appearance	High temperature resistance (up to 800°C)
Strong sparkling brilliance in comparison to other gold tones within the same particle size range	Multilayer technology

ORDERING INFORMATION

Product	Color	Packaging size
KC9820G	Gold pearlescent	samples, 25 kg

PRODUCT INFORMATION

Composition	Chemical Name	Specification	CAS no.
	Synthetic Mica	41-45 %	12003-38-2
	Titanium Oxide (TiO ₂)	21-25 %	13463-67-7
	Iron (III) Oxide (Fe ₂ O ₃)	30-34 %	1309-37-1
	Tin Oxide (SnO ₂)	1-3 %	18282-10-5
Particle size distribution	10-45 μm		
pH value	7.0 -10.0	ISO787-9	
Oil absorption	60-80 g/100 g	GB 5211.15-88	
Density	2.8-3.4 g/cm ³	KC Method	

Fujian Kuncai Material Technology Co. Ltd.,
Haicheng Rd., Yuanhong Investment Zone, Fuqing
ZIP: 350314, China, T: +86 (0) 591-855 883 38
Mail: sales@fjkuncai.com
www.fjkuncai.com

Kuncai Europe B.V.
Radeweg 3, 8171 MD Vaassen, The Netherlands,
T: +31 (0) 578-569 605
Mail: customerservice@kuncaieurope.com
www.kuncaieurope.com

Kuncai Americas LLC,
130 E. Wilson Bridge Rd Suite 210, Worthington,
OH 43035, USA, T: +001 (0) 614-547-7424
Mail: customerservice@kuncaius.com
www.kuncaius.com